

APICAL® 300 AV



APICAL polyimide film possesses an excellent balance of physical, thermal, electrical and chemical properties over a wide range of temperatures (-269°C [752°F]). More precise thickness control, superior web flatness, plus improved adhesion and excellent dimensional stability are standard features with Apical polyimide films.

Major Applications

- Polyimide base materials for FPC.
- Motor generator insulation.
- Wire and cable insulation
- Barcode label.
- Pressure sensitive tape
- Specialty Fabricated Parts

Construction

Items	Mils	Microns
Nominal Thickness	3.0	76.2
PI	3.0	76.2

Mechanical Properties

Items	Units	Test Method
Tensile Strength MD, kpsi (MPa)	31 (213)	ASTM D882
Tensile Strength TD, kpsi (MPa)	32 (223)	ASTM D882
Tensile Modulus MD, kpsi (GPa)	300 (2.1)	ASTM D882
Tensile Modulus TD, kpsi (GPa)	315 (2.2)	ASTM D882
Elongation MD (TD), %	104 (101)	ASTM D882

Thermal Properties

Items	Units	Test Method
Heat Shrinkage MD %	0.05	200 dC – 2 hrs
Heat Shrinkage TD %	0.04	200 dC – 2 hrs
Coefficient of Thermal Expansion MD, ppm/dC dC	32	TMA 100–200
Coefficient of Thermal		

Expansion TD, ppm/dC dC	31	TMA 100–200
----------------------------	----	-------------

Electrical Properties

Items Method	Units	Test
Dielectric Strength, KV/mil	5.1	ASTM D149
Dielectric Constant, 1kHz	3.2	ASTM D150
Dissipation Factor, 1kHz	0.0019	ASTM D150
Volume Resistivity, Ohm-cm	>1E+16	ASTM D257

Physical Properties

Items Method	Units	Test
Water Absorption, %	2.7	IPC-TM650-2.6.2
Coefficient of Humidity Expansion Typical, ppm/%RH	16	HMA
Density, g/cm ³	1.42	ASTM D1505
Yield, ft ² /lb (m ² /kg)	47(9)	

The data noted in these technical data sheets are given as examples and are not intended to be read as guaranteed values .

KANEKA NORTH AMERICA APICAL DIVISION

6161 UNDERWOOD ROAD

PASADENA, TEXAS 77507

800-222-8128 FAX 800-562-5284

www.kaneka.com

kaneka