

# APICAL® L50S10PL



APICAL® Polyimide possesses an excellent balance of Physical, Thermal, Electrical and Chemical properties over a wide range of temperatures (-269°C [-452°F] to 400°C [752°F]). More precise thickness control, superior web flatness, plus improved adhesion and excellent dimensional stability are standard features with APICAL® Polyimide film.

## Applications

- Aircraft Wire and Cable
- Magnet Wire
- Traction Equipment
- Down Hole Motors
- Mining Equipment

## Characteristics

- Improved Bond/Peel Strengths
- Ideal Elongation
- Optimal Flexibility
- Excellent Dielectric Properties

## Typical Properties for L50S10PL

Apical® Fluoropolymer Coated Polyimide Film **Electroimide®**

Mechanical	
Property	L50S10PL
Tensile Strength MD, kpsi	26
% Elongation to break MD	103
Heat Seal Strength FP-PI, g/in @ 350°C, 20sec, 20psi	1600
Specific Gravity, g/cm <sup>3</sup>	1.79
Yield, ft <sup>2</sup> /lb	90.50
Yield, g/m <sup>2</sup>	60.35
Thickness, mil (microns) – total	1.5 (38.1)
Thickness, mil (microns) Polyimide AV	1.00 (25.4)
Thickness, mil (microns) FP	0.50 (12.7)

Thermal	
Property	L50S10PL
Melt Point of FP, °C	270
Flammability, UL rating	V-0
UL Relative Thermal Index, Electrical, °C	240
UL Relative Thermal Index, Mech., °C	210

Electrical	
Property	L50S10PL
Dielectric Strength, V/mil	5200
Dielectric Constant @ 1kHz	2.7
Dissipation Factor @ 1kHz	0.0035
Volume Resistivity, Ohm-cm	> 10 <sup>16</sup>
UL Hot Wire Ignition rating	0
UL High Voltage Arc Tracking	4
UL D495 rating	7
UL Comparative Tracking Index	3
UL High Current Arc Ignition rating	4

Chemical	
Property	L50S10PL
Moisture Absorption, water soak, % 24hrs	1.6
Hydroscopic Coefficient of Expansion, ppm / % RH	9

The data noted in these technical data sheets are given as examples and are not intended to be read as guaranteed values.

## Safety Precautions

Before using the laminated film **read the MSDS supplied** and the “**Guide to Safe Handling of Fluoropolymer resins**” which can be found online.

The conditions of your use and application of our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. This application-specific analysis at least must include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done at Kaneka Texas Corporation®. All information is given without warranty or guarantee. It is expressly understood and agreed that customer assumes and hereby expressly releases Apical Division of Kaneka Texas Corporation from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance and information. Any statement or recommendation not contained herein is unauthorized and shall not bind Apical Division of Kaneka Texas Corporation. Nothing herein shall be construed as a recommendation to use any product in conflict with patents covering any material or its use. No license is implied or in fact granted under the claims of any patent.  
Email: [www.kaneka.com](http://www.kaneka.com)®

**KANEKA NORTH AMERICA APICAL DIVISION**  
6161 UNDERWOOD ROAD  
PASADENA, TEXAS 77507  
800-222-8128 FAX 800-562-5284  
[www.kaneka.com](http://www.kaneka.com)

**KANEKA**

